




Paste pigmentate per prodotti vernicianti



LOW 800

PIGMENT DISPERSIONS LOW 800 SERIES

DISPERSIONS MEDIUM •

Low VOC long-oil Alkyd Resin, not inflammable (60°C<flash point<93°C).

COMPATIBILITY •

Long and medium oil alkyds, including urethanised version, linseed oil and stand-oil, blend of drying oils or not-drying oils, one or two-components in different mixture ratios.

MAIN APPLICATIONS •

Formulations of paint products for parquet sector, furniture, doors and windows frame. Suitable for obtaining semi-transparent colours and colours able to give a pleasant and uniform effect to the threatened article. Once dried, they can be over-painted with various finishes (polyurethane, acrylic and water-based paints).

Conformi alla normativa UNI EN ISO 3679:2015, esenti da classificazione ADR.

CODE	PIGMENT TYPE	Colour Index	% p Pigment	% p Binder	% p Solid
LOW 800	Titanium Dioxide	P.W. 6	70	15	85
LOW 807	Yellow Iron Oxide	P.Y. 42	50	34	84
LOW 812	Red Iron Oxide	P.R. 101	65	26	91
LOW 844	Transparent Yellow Iron Oxide	P.Y. 42	35	38	73
LOW 805	Transparent Red Iron Oxide	P.R. 101	35	38	73
LOW 848B	Transparent Brown Iron Oxide	P.R. 101	45	31	76
LOW 820	Arylamide Yellow	P.Y. 74	35	43	78
LOW 821	Ditroaniline Orange	P.O. 5	25	58	83
LOW 808	Manganese 2B Toner	P.R. 48:4	25	52	77
LOW 857	DDP Red	P.R. 254	25	43	68
LOW 841	Dioxazine Violet	P.V. 23	10	67	77
LOW 804	Blue Beta Copper Phtalocyanine NCNF	P.B. 15:4	25	49	79
LOW 856	Blue Alpha Copper Phtalocyanine NCNF	P.B. 15:2	20	59	79
LOW 836	Green Chlorinated Copper Phtalocyanine	P.G. 7	20	59	79
LOW 897	Medium Jetness Black MCF	P.BI. 7	20	59	79
LOW 898	Tinting black LCF	P.BI. 7	20	58	78
LOW 899	High Jetness Black HCF	P.BI. 7	12	66	78

Above data are to be considered nominal values; variations values are possible during the testing process on "colour and tinting strength".

NOTE: paste performance in specified products depend on possible "relation" between all the components in a formula so we always suggest an accurate verification in compatibility test.



Codice Fiscale e Partita Iva: 04616660017
Capitale Sociale Euro 100.980 i.v. – R.E.A. TO 644862 – Registro imprese 1657/84
Sede legale, amministrativa e operativa: Via Moncalieri 99/15D – Frazione Tetti Caglieri – 10048 VINOVO (TO) – Italia
Tel. +39 011 993 11 09
email: direzione@abchimica.it
www.abchimica.it